HENAN REBO COMPOSITE MATERIALS CO., LTD.
Chaohua Industry Zone, Xinmi City 452385, Henan Province, China

ACID-RESISTANCE BRICK

FEATURES

High acid and alkali resistance
Low water absorption
Not easy to oxidize at room temperature
Not easy to be contaminated by the medium

CHEMICAL ANALYSIS

Al_2O_3	20-30%
Fe_2O_3	0.5-3%
SiO_2	60-70%

Remark: The chemical content data represent average reference.

TECHNICAL PROPERTIES

Acid resistant	≥ 99.8 %
Bulk density	2.3g/cm³
Water absorption	≤ 0.5%
Bending strength	≥ 40 MPa

Email: market@rebo-refra.com Mob.: 0086 132 13092812 Web: acidproofbrick.com